

Product Weight Conversions for KYDEX® sheet

For information applicable to KYDEX® FST please refer to 300 series technical briefs.

TB - 101-B

Conversion Table:

Product Weight Conversion Factors Domestic Price List

Product		KYDEX® 110, 110 MB, XD03	KYDEX® 321	KYDEX® FST	KYDEX® 100, 311, 311 MB, 331, 331d, 6185, T, T MB, V, V103, XD, XD MB	KYDEX® 152 WG	KYDEX® 6200, 6200d	KYDEX® 6565	KYDEX® 5555, 5555 MB
Specific Gravity g/cm ³		1.31	1.33	1.34	1.35	1.37	1.40	1.48	1.52
Thickness		lbs / sq ft							
inches	mm								
0.028	0.7	0.1908	0.1937	0.1952	0.1966	0.1996	0.2039	0.2156	0.2214
0.040	1.0	0.2726	0.2768	0.2788	0.2809	0.2851	0.2913	0.3080	0.3163
0.060	1.5	0.4089	0.4151	0.4183	0.4214	0.4276	0.4370	0.4620	0.4745
0.080	2.0	0.5452	0.5535	0.5577	0.5619	0.5702	0.5827	0.6160	0.6326
0.093	2.4	0.6338	0.6435	0.6483	0.6532	0.6628	0.6773	0.7160	0.7354
0.100	2.5	0.6815	0.6919	0.6971	0.7023	0.7127	0.7283	0.7699	0.7908
0.118	3.0	0.8042	0.8165	0.8226	0.8287	0.8410	0.8594	0.9085	0.9331
0.125	3.2	0.8519	0.8649	0.8714	0.8779	0.8909	0.9104	0.9624	0.9884
0.156	4.0	1.0631	1.0794	1.0875	1.0956	1.1118	1.1362	1.2011	1.2336
0.187	4.7	1.2744	1.2939	1.3036	1.3133	1.3328	1.3620	1.4398	1.4787
0.197	5.0	1.3426	1.3631	1.3733	1.3836	1.4041	1.4348	1.5168	1.5578
0.236	6.0	1.6084	1.6329	1.6452	1.6575	1.6820	1.7188	1.8171	1.8662
0.250	6.4	1.7038	1.7298	1.7428	1.7558	1.7818	1.8208	1.9249	1.9769
0.276	7.0	1.8810	1.9097	1.9240	1.9384	1.9671	2.0102	2.1250	2.1825
0.312	7.9	2.1263	2.1588	2.1750	2.1912	2.2237	2.2724	2.4022	2.4672
0.325	8.3	2.2149	2.2487	2.2656	2.2825	2.3163	2.3671	2.5023	2.5700
0.375	9.5	2.5556	2.5947	2.6142	2.6337	2.6727	2.7312	2.8873	2.9653

General Conversion Factor for Any Thickness (see below)

lbs / ft ² / mil	0.006815	0.006919	0.006971	0.007023	0.007127	0.007283	0.007699	0.007908
kg / m ² / mm	1.31	1.33	1.34	1.35	1.37	1.40	1.48	1.52

KYDEX, LLC

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Outside the US: +1.570.389.5814
 Fax: 800.452.0155, +1.570.387.7786
 Email: info@kydex.com

Technical Service

Phone: 800.682.8758
 Fax: +1.570.387.8722
 Outside the US: +1.570.387.6997
 Email: techservice@kydex.com

www.kydex.com

For any thickness: To convert to lbs/ft², use the
General Conversion Factor
 for that Product:

EXAMPLE: KYDEX® 100 0.093"(2.36mm) sheet:
 0.007023 x 93 mils = .6532 lbs / ft²
 1.35 x 2.36mm = 3.186 kg / m²
 *Take any Specific Gravity (kg/m³/mm) and divide by 192.22 to get lbs/ft²/mil

1 lb = .45359 kg
1 kg = 2.2046 lb
1 ft ² = .0929 m ²
1 m ² = 10.76439 ft ²

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.