

Minimum Service Temperature of KYDEX® Thermoplastic Sheet

TB - 121-B

Introduction

At room temperature, most plastics exhibit their typical properties as listed on the technical data sheets. This includes the plastic's ability to withstand impacts without cracking or failing as conveyed through Izod or Drop Dart impact values. As the temperature decreases most plastics rapidly lose this ability to resist cracking and become brittle. Low temperatures are typically more harmful to plastics and their surroundings than high temperatures because this is where shattering occurs as opposed to deformation at high temperatures. This is sometimes referred to as the Glass Transition Temperature or Tg. Tg for plastics often refers to the temperature region where plastics exhibit 50% brittle failures as opposed to a flexible or ductile failure (the region where the polymer exhibits brittle failures similar to glass).

Tg varies greatly between polymers and can be changed dramatically when modified with certain additives. Tg is not usually a specific temperature, but often a range where the plastic begins to exhibit brittle failures to the point where all brittle failures occur. After a plastic falls below this temperature, there is little change to the polymer and inherent impact properties will determine the strength of the plastic. It is important to note that Tg does not specify a low service temperature limit but simply indicates the point where a brittle fracture is the dominant failure type.

KYDEX® sheet, like all other thermoplastics becomes brittle at lower temperatures. Below are two tables that show typical impact values for several grades of KYDEX® sheet at various temperatures.

Table 1

Table 1 shows typical values for Notched Izod Impact as per ASTM D256 at 3.18mm (0.125") thick. At -29.0°C (-20°F) KYDEX® sheet exhibits all brittle breaks. Below this temperature, the impact does not drop much further. The Notched Izod test requires a 2.54mm (0.100") deep notch be cut into the sample that is then struck with a swinging pendulum. This type of impact would more closely match a part that is already fractured and then experiences an additional impact. The results of this test method are mainly used to compare one plastic to another under very controlled test parameters and are very difficult to transfer to real-life situations.

Product	73°F (23°C)	-20°F (-29°C)
KYDEX® 100	18.0 ft-lb/in (961 J/m)	1.5 ft-lb/in (80 J/m)
KYDEX® 311/311MB/312	12.0 ft-lb/in (641 J/m)	1.0 ft-lb/in (53 J/m)
KYDEX® 331/331d	12.0 ft-lb/in (641 J/m)	1.0 ft-lb/in (53 J/m)
KYDEX® 430	3.4 ft-lb/in (182 J/m)	1.3 ft-lb/in (69 J/m)
KYDEX® T	15.0 ft-lb/in (801 J/m)	2.8 ft-lb/in (149 J/m)

Typical Notched Izod Values at Various Temperatures
ASTM D-256

KYDEX, LLC

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@kydex.com

Technical Service

Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
Email: techservice@kydex.com

www.kydex.com

Minimum Service Temperature of KYDEX® Thermoplastic Sheet

TB - 121-B

Table 2

Table 2 shows typical values for Gardner Dropdart Impact as per ASTM D5420, Geometry GE, 3.18mm (0.125") thick at -20°F (-29°C). A dropdart impact comes closest to a realistic impact that a part may experience in daily use.

KYDEX® sheet has been used in many cold temperature applications successfully without incident. With the proper part design, selected thickness, and product choice, it can be used for many cold temperature applications successfully.

Note: It is important to test KYDEX® sheet in the appropriate environment to verify its suitability.

Product	73°F (23°C)	-20°F (-29°C)
KYDEX® 100	576 in-lbf (65.1 J)	54 in-lbf (6.1 J)
KYDEX® 311/311MB/312	>625 in-lbf (70.6 J)	197 in-lbf (22.3 J)
KYDEX® 331/331d	>625 in-lbf (70.6 J)	197 in-lbf (22.3 J)
KYDEX® 430	581 in-lbf (65.6 J)	52 in-lbf (5.9 J)
KYDEX® T	>627 in-lbf (70.8 J)	92 in-lbf (10.4 J)

Typical Dropdart Values at Various Temperatures
ASTM D-5420, Geometry GE, 3.18mm (0.125")

KYDEX, LLC
ISO 9001 and 14001 Certified

Customer Service
6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@kydex.com

Technical Service
Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
Email: techservice@kydex.com

www.kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.